



compes@wanadoo.fr



Tél. : 04 37 06 21 50
Fax : 04 37 06 21 51

ANALYSES TECHNIQUES ET MECANIQUES :

Désignation	Etat	Rm	Allongement % mini			Dureté
		N/mm ²	A80	A50	LO 5 dO	HRB
FE RIC	Recuit	270/350	38	40	40	58 max
FE P01	Plusieurs passages après recuit et laminage	410 max	24	26	28	65/74
FE 390		390/490	-	-	-	72/83
FE 490		490/590	-	-	-	84/93
FE 590	Laminé sans recuit	> 590	-	-	-	> 90