



DURETE :

PRODUIT LAMINE ET RECUIT		PRODUIT LAMINE, RECUIT, et SKINPASSE								PRODUIT LAMINE A FROID		ACIER	
RECUIT		FE PO1		FE 390		FE 490		FE 590		FE 590			
RECUIT FINAL		DOUX		½ DOUX		½ ECROUI		ECROUI		ECROUI			
HRB	R Kg/mm ² *	HRB	R*	HRB	R*	HRB	R*	HRB	R*	HRB	R*	HRB	R*
		65	36	74	41	84	51	93,5	61	85	57	10	67
		65,5	-	75	42	85	52	94	62	86	58	12	70,5
		66	36,5	76	43	86	53	94,5	63	87	59	14	75,5
		66,5	-	77	44	87	54	95	64	88	60,5/61	16	79,2
		66	36,5	75	42	85	52	94	62	86	62	18	82,8
		67	37	78	45	88	55	95,5	65	89	62	18	82,8
		67,5	37,5	79	46	89	56	96	66	90	63	20	86,4
		68	-	80	47	90	57	96,5	67	91	64,5/65	22	90
		68,5	38	81	48	91	58	97	68	92	66	23	92
		69	-	82	49	92	59	97,5	69	93	67	25	97
		69,5	38,5	83	50	93	60	98	70	94	68	27	101
		70	-							95	70	29	106,2
		70,5	39							96	71,5/72	31	111,5
		71	-							97	73,5/74	32	113,5
		71,5	39,5							98	74,5/75	34	119,4
		72	40							99	76,5/77	36	124,2
		72,5	-							100	78	38	129,6
		73	40,5							101	80	40	135,7
		73,5	-							102	82	42	143,2
		74	41							103	84	44	150,4
										104	87	45	153,5
										105	90	47	161,5
										106	92	49	171,5
										107	95	51	181
										108	99	53	191
										109	103	55	199,8
										110	107	57	211,7